

# TECHNICAL DATA

## POLYESTER FILM TAPE

**Product Code: 1P800**

*P. Leo & Co (B. C.) Ltd.*

150-12820 Clarke Place, Richmond, B.C. V6V 2H1, Canada

Telephone : (604)270-6115 \* Facsimile : (604)538-2909 \* E-mail : sales@pleo.com

Web Site : <http://www.pleo.com>



UL FILE #E126174

**Description:** 1P800 is a polyester film coated with a pressure sensitive Acrylic adhesive, high dielectric strength, excellent adhesive properties, good chemical and Solvent resistant.

**Application:** For use as electrical insulation, in all types of coils and transformers and other uses requiring good insulation and moisture resistance. It is used as insulation material of class B.

**Technical Details:**

<u>PROPERTIES</u>	<u>UNITS</u>	<u>SPECIFICATION</u>
COLOR	-	*see below
TOTAL THICKNESS	mm	0.055±0.005
TENSILE STRENGTH	kg/25mm	10
ELONGATION	%	70
ADHESION TO STEEL	kg/25mm	0.8
DIELECTRIC BREAKDOWN	kV	4.5
TEMPERATURE CLASS	° C	130

\* Color: TR = transparent      RD = red      YE = yellow  
BK = black      BL = blue      WH = white  
GR = green

**Test Method:** In accordance with ASTM method

**Shelf Life:** 6 months when storage at 73F and 65% relative humidity

**Availability:** Standard 50M rolls, 3" core, width 970mm

### **Important Notice to Purchase**

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or the inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection therewith.

No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of Seller and manufacturer.